

The integrity of sealing of ampoules should be assessed on an individual basis. With dye intrusion, the ampoules are submerged in a dye solution and under an applied vacuum. Two techniques are available that depend on dye ingress under vacuum or electronic means. Any container that has cracks in its structure or is not sealed will admit the dye when the vacuum is reduced. On washing, badly sealed ampoules will be coloured.